



Designation: A210/A210M – 19

# Standard Specification for Seamless Medium-Carbon Steel Boiler and Superheater Tubes<sup>1</sup>

This standard is issued under the fixed designation A210/A210M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope\*

1.1 This specification<sup>2</sup> covers minimum-wall-thickness, seamless medium-carbon steel, boiler tubes and boiler flues, including safe ends (see **Note 1**), arch and stay tubes, and superheater tubes.

**NOTE 1**—This type is not suitable for safe ending by forge welding.

1.2 The tubing sizes and thicknesses usually furnished to this specification are ½ in. to 5 in. [12.7 to 127 mm] in outside diameter and 0.035 to 0.500 in. [0.9 to 12.7 mm], inclusive, in minimum wall thickness. Tubing having other dimensions may be furnished, provided such tubes comply with all other requirements of this specification.

1.3 Mechanical property requirements do not apply to tubing smaller than ⅛ in. [3.2 mm] in inside diameter or 0.015 in. [0.4 mm] in thickness.

1.4 This specification covers grades A-1 and C of Seamless Medium-Carbon Boiler and Superheater Tubes with different chemical and tensile requirements. (**Table 1**, **Table 3**, and **Section 11**.)

1.5 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other. Combining values from the two systems may result in nonconformance with the specification. The inch-pound units shall apply unless the “M” designation of this specification is specified in the order.

1.6 *This international standard was developed in accordance with internationally recognized principles on standardization established in the Decision on Principles for the Development of International Standards, Guides and Recommendations issued by the World Trade Organization Technical Barriers to Trade (TBT) Committee.*

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.09 on Carbon Steel Tubular Products.

Current edition approved May 1, 2019. Published May 2019. Originally approved in 1938. Last previous edition approved in 2012 as A210/A210M – 02 (2012). DOI: 10.1520/A0210\_A0210M-19.

<sup>2</sup> For ASME Boiler and Pressure Vessel Code applications see related Specification SA-210 in Section II of that Code.

## 2. Referenced Documents

2.1 *ASTM Standards*:<sup>3</sup>

A450/A450M Specification for General Requirements for Carbon and Low Alloy Steel Tubes

## 3. Ordering Information

3.1 Orders for material under this specification should include the following, as required, to describe the desired material adequately:

3.1.1 **Quantity** (feet, metres, or number of lengths),

3.1.2 **Name of material** (seamless tubes),

3.1.3 **Grade**,

3.1.4 **Manufacture** (hot-finished or cold-finished),

3.1.5 **Size** (outside diameter and minimum wall thickness),

3.1.6 **Length** (specific or random),

3.1.7 **Optional requirements** (Sections 7 and 10),

3.1.8 **Test report required**, (see Certification Section of Specification A450/A450M),

3.1.9 **Specification designation**, and

3.1.10 **Special requirements**.

## 4. General Requirements

4.1 Material furnished under this specification shall conform to the applicable requirements of the current edition of Specification A450/A450M, unless otherwise provided herein.

## 5. Manufacture

5.1 *Steelmaking Practice*—The steel shall be killed.

5.2 The tubes shall be made by the seamless process and shall be either hot-finished or cold-finished, as specified.

## 6. Heat Treatment

6.1 Hot-finished tubes need not be heat treated. Cold-finished tubes shall be given a subcritical anneal, a full anneal, or a normalizing heat treatment after the final cold finishing process.

<sup>3</sup> For referenced ASTM standards, visit the ASTM website, [www.astm.org](http://www.astm.org), or contact ASTM Customer Service at [service@astm.org](mailto:service@astm.org). For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

\*A Summary of Changes section appears at the end of this standard



TABLE 1 Chemical Requirements

Element	Composition, %	
	Grade A-1	Grade C
Carbon <sup>A</sup> , max	0.27	0.35
Manganese	0.93 max	0.29–1.06
Phosphorus, max	0.035	0.035
Sulfur, max	0.035	0.035
Silicon, min	0.10	0.10

<sup>A</sup> For each reduction of 0.01 % below the specified carbon maximum, an increase of 0.06 % manganese above the specified maximum will be permitted up to a maximum of 1.35 %.

TABLE 3 Tensile Requirements

	Grade A-1	Grade C
Tensile strength, min, ksi [MPa]	60 [415]	70 [485]
Yield strength, min, ksi [MPa]	37 [255]	40 [275]
Elongation in 2 in. or 50 mm, min, %	30	30
For longitudinal strip tests, a deduction shall be made for each 1/32-in. [0.8-mm] decrease in wall thickness under 5/16 in. [8 mm] from the basic minimum elongation of the following percentage points	1.50 <sup>A</sup>	1.50 <sup>A</sup>
When standard round 2-in. or 50-mm gage length or smaller proportionally sized specimen with the gage length equal to 4D (four times the diameter) is used	22	20

<sup>A</sup> See Table 4 for the computed minimum values.

## 7. Surface Condition

7.1 If pickling or shot blasting or both are required, this shall be specifically stated in the order.

## 8. Chemical Composition

8.1 The steel shall conform to the requirements as to chemical composition prescribed in Table 1.

8.2 When a grade is ordered under this specification, supplying an alloy grade that specifically requires the addition of any element other than those listed for the ordered grade in Table 1 is not permitted.

## 9. Product Analysis

9.1 When requested on the purchase order, a product analysis shall be made by the supplier from one tube or billet per heat. The chemical composition thus determined shall conform to the requirements specified.

9.2 If the original test for product analysis fails, retests of two additional billets or tubes shall be made. Both retests for the elements in question shall meet the requirements of the specification; otherwise, all remaining material in the heat or lot (see Note 2) shall be rejected or, at the option of the producer, each billet or tube may be individually tested for acceptance. Billets or tubes which do not meet the requirements of the specification shall be rejected.

NOTE 2—For flattening and flaring requirements, the term “lot” applies to all tubes prior to cutting of the same nominal size and wall thickness which are produced from the same heat of steel. When final heat treatment is in a batch-type furnace, a lot shall include only those tubes of the same size and from the same heat which are heat treated in the same furnace charge. When the final heat treatment is in a continuous furnace, the number of tubes of the same size and from the same heat in a lot shall be

determined from the size of the tubes as prescribed in Table 2.

NOTE 3—For tensile and hardness test requirements, the term “lot” applies to all tubes prior to cutting, of the same nominal diameter and wall thickness which are produced from the same heat of steel. When final heat treatment is in a batch-type furnace, a lot shall include only those tubes of the same size and the same heat which are heat treated in the same furnace charge. When the final heat treatment is in a continuous furnace, a lot shall include all tubes of the same size and heat, heat treated in the same furnace at the same temperature, time at heat, and furnace speed.

## 10. Tensile Requirements

10.1 The material shall conform to the requirements as to tensile properties prescribed in Table 3.

10.2 Table 4 gives the computed minimum elongation values for each 1/32-in. [0.8-mm] decrease in wall thickness. Where the wall thickness lies between two values shown above, the minimum elongation value shall be determined by the following equation:

$$E = 48t + 15.00 \quad [E = 1.87t + 15.00]$$

where:

$E$  = elongation in 2 in. or 50 mm, %, and  
 $t$  = actual thickness of specimen, in. [mm].

## 11. Hardness Requirements

11.1 The tubes shall have a hardness not exceeding the following: 79 HRBW or 143 HBW for Grade A-1, 89 HRBW or 179 HBW for Grade C.

## 12. Mechanical Tests Required

12.1 *Tension Test*—One tension test shall be made on a specimen for lots of not more than 50 tubes. Tension tests shall be made on specimens from two tubes for lots of more than 50 tubes (see Note 3).

12.2 *Flattening Test*—One flattening test shall be made on specimens from each end of one finished tube from each lot (see Note 2), but not the one used for the flaring test. Tears or breaks occurring at the 12 or 6 o'clock positions on Grade C tubing with sizes of 2.375 in. [60.3 mm] in outside diameter and smaller shall not be considered a basis for rejection.

12.3 *Flaring Test*—One flaring test shall be made on specimens from each end of the one finished tube from each lot (see Note 2), but not the one used for the flattening test.

12.4 *Hardness Test*—Brinell or Rockwell hardness tests shall be made on specimens from two tubes from each lot (see Note 3).

TABLE 2 Number of Tubes in a Lot Heat Treated by the Continuous Process

Size of Tube	Size of Lot
2 in. (50.8 mm) and over in outside diameter and 0.200 in. (5.1 mm) and over in wall thickness	not more than 50 tubes
2 in. (50.8 mm) and over in outside diameter and under 0.200 in. (5.1 mm) in wall thickness	not more than 75 tubes
Less than 2 in. (50.8 mm) but over 1 in. (25.4 mm) in outside diameter	not more than 75 tubes
1 in. (25.4 mm) or less in outside diameter	not more than 125 tubes



TABLE 4 Computed Minimum Elongation Values

Wall Thickness, in. [mm]	Elongation in 2 in. or 50 mm, min, % <sup>A</sup>
5/16 (0.312) [8]	30
3/32 (0.281) [7.2]	28
1/4 (0.250) [6.4]	27
7/32 (0.219) [5.6]	26
3/16 (0.188) [4.8]	24
5/32 (0.156) [4]	22
1/8 (0.125) [3.2]	21
3/32 (0.094) [2.4]	20
1/16 (0.062) [1.6]	18
0.062 to 0.035 [1.6 to 0.9], excl	17
0.035 to 0.022 [0.9 to 0.6], excl	16
0.022 to 0.015 [0.6 to 0.4], incl	16

<sup>A</sup> Calculated elongation requirements shall be rounded to the nearest whole number.

12.5 *Hydrostatic or Nondestructive Electric Test*—Each tube shall be subjected to the hydrostatic, or, instead of this test, a nondestructive electric test may be used when specified by the purchaser.

### 13. Forming Operations

13.1 When inserted in the boiler, tubes shall stand expanding and beading without showing cracks or flaws. When properly manipulated, superheater tubes shall stand all forging, welding, and bending operations necessary for application without developing defects.

### 14. Product Marking

14.1 In addition to the marking prescribed in Specification A450/A450M, the marking shall indicate whether the tube is hot-finished or cold-finished.

14.2 *Bar Coding*—In addition to the requirements in 14.1 bar coding is acceptable as a supplemental identification method. The purchaser may specify in the order a specific bar coding system to be used.

### 15. Keywords

15.1 boiler tubes; carbon; seamless steel tube; steel tube; superheater tubes

## SUMMARY OF CHANGES

Committee A01 has identified the location of selected changes to this specification since the last issue, A210/A210M – 02 (2012), that may impact the use of this specification. (Approved May 1, 2019.)

- (1) Scope was expanded to include grades.
- (2) Hardness values were aligned to match changes in A370 Sections 16–18 reporting of hardness values.

*ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.*

*This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.*

*This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org). Permission rights to photocopy the standard may also be secured from the Copyright Clearance Center, 222 Rosewood Drive, Danvers, MA 01923, Tel: (978) 646-2600; http://www.copyright.com/*