

schedule 140 for Plain-End Pipe
(Data from ASME B36.10 (incorporating ASTM A53 Table 2.2))

DN	NPS	Outside Diameter		Wall Thickness		Plain End Mass		Identification	Schedule No.
		mm	in	mm	in	kg/m	lb/ft		
250	10	273.0	10.750	25.4	1.000	155.10	104.23	XXS	140
300	12	323.8	12.750	28.58	1.125	208.08	139.81		140
350	14	355.6	14.000	31.75	1.250	253.58	170.37		140
400	16	406.4	16.000	36.53	1.438	333.21	223.85		140
450	18	457	18.000	39.67	1.562	408.28	274.48		140
500	20	508	20.000	44.45	1.750	508.15	341.41		140
550	22	559	22.000	47.63	1.875	600.67	403.38		140
600	24	610	24.000	52.37	2.062	720.19	483.57		140